Proposal:	4-05-629		Council: 4/2015			
Title:	Magnetic excitations in the $S=1/2$ kagome antiferromagnet and quantum spin liquid candidate `Mg-herbertsmithite', $M_{2}C_{12}(OD) \in C_{12}$					
Research area: Physics						
This proposal is a new proposal						
Main proposer	: Andrew S. WILLS					
Experimental team: Bjorn FAK						
Local contacts:	Jacques OLLIVIER					
Samples: MgCu3(OD)6Cl2						
Instrument		Requested days	Allocated days	From	То	
IN5		4	4	03/12/2015	07/12/2015	
Abstract:	1.1		·			

We propose to study the magnetic excitations in the quantum spin liquid (QSL) candidate 'Mg-herbertsmithite', which forms a geometrically perfect and highly frustrated 2D kagome lattice of S=1/2 quantum spins with dominant antiferromagnetic nearest-neighbor interactions. No long-range order is observed down to T=20 mK and recent theoretical work predicts a rich phase diagram with different types of gapless, chiral and U(1) quantum spin liquids that await experimental confirmation. The measurements aim at determining the nature of the excitations, which could be bosonic quasiparticles forming a discrete excitation spectrum or fractionalized fermionic quasiparticles forming a continuum, which could be gapped or not.

Magnetic excitations in the S = 1/2 kagome antiferromagnet and quantum spin liquid candidate 'Mg-herbertsmithite', γ -MgCu₃(OD)₆Cl₂

The search for quantum spin liquids (QSLs) is a cornerstone of condensed matter physics. These are new and exotic states of matter that in two dimensions were proposed by Anderson to underpin the transition to unconventional superconductivity of the high- $T_{\rm C}$ cuprates [1]. Formed by geometric frustration of a magnetic lattice and the quantum fluctuations that are maximal for S = 1/2 spins, QSLs do not break symmetry as conventional magnets do, but are instead characterised by dynamic short-range correlations and fractionalised excitations [2,3]. The S = 1/2 kagome antiferromagnet (KAFM) is considered the most promising model system for the realisation of 2D QSLs.

Despite the importance of such systems, good experimental examples are rare. Much effort has been focused on the paratacamite family of minerals, $Cu_3(Cu,Zn)(OH)_6Cl_2$, and in particular the S = 1/2 KAFM herbertsmithite, γ -Cu₃Zn(OH)₆Cl₂ [3–5]. Since its discovery, several factors such as Cu/Zn inter-site mixing and Dzyaloshinski-Moriya (DM) antisymmetric exchange have been found to occur. Inter-site mixing within herbertsmithite couples the kagome planes, destroys the 2-dimensionality of the system and introduces an additional term into the Hamiltonian that acts to relieve the frustration. Extracting the intrinsic physics of the S = 1/2 KAFM is therefore complicated, although recent experiments have found several hallmarks of a quantum spin liquid ground state [3].

Interest in paratacamite based materials as model S = 1/2 KAFMs has grown further with the discoveries of kapellasite, α -Cu₃Zn(OH)₆Cl₂, a polymorph of herbertsmithite, and its magnesium analogue haydeeite, α -Cu₃Mg(OH)₆Cl₂ [6,7]. In these materials, the kagome lattice is constructed by regular doping of a triangular lattice of Cu²⁺ with Mg²⁺ or Zn²⁺ ions, as opposed to the 3-dimensional parent pyrochlore lattice in herbertsmithite. As such, any antisite disorder between the divalent cation sites in both haydeeite and kapellasite cannot introduce 3-dimensionality into the magnetic system. In haydeeite, the ground-state and the excitations measured recently by INS experiments are in agreement with theoretical predictions of a classical multi-exchange model on the S = 1/2 kagome lattice [8,9]. In the closely related paratacamite member kapellasite, INS revealed unique QSL behaviour with dynamic short-range gapless excitations that are consistent with a non-coplanar cuboc2 magnetic ground state [2].

Here, we focused on another member of the paratacamite family, 'Mg-herbertsmithite', γ -MgCu₃(OH)₆Cl₂, which has not yet attracted much attention. This material is isoelectronic and isostructural with herbertsmithite and possesses a similar degree of magnetic frustration (Figure 1a). Despite strong mean-field antiferromagnetic interactions, $\theta_{\rm W} = -284$ K, μ SR experiments do not detect any long-range magnetic order down to T = 20 mK, giving a record frustration index $f = \theta_{\rm W}/T_{\rm N} > 10000$, whilst the low-T spin dynamics are consistent with a QSL ground-state (Figure 1b) [7,10].

The experiment was carried out on IN5 using 4 g of fully deuterated powder sample of γ -MgCu₃(OH)₆Cl₂ in annular geometry in an orange cryostat. Measurements were performed at temperatures of T = 1.5, 6, 12, 50, and 125 K using several wavelengths in the cold neutron range. Typical counting times were 7 to 14 hours per run. From the very preliminary data reduction of the experiment carried out last December (Figure 1c), a clear quantum spin liquid response is observed that extends to energies well beyond those that are easily accessible on IN5.



Figure 1: (a) Crystal structure of 'Mg-herbertsmithite. (b) Muon polarisation. (c) Dynamic structure factor of 'Mg-herbertsmithite' showing clear spin-liquid scattering for Q < 1.4 Å⁻¹. Spurious features are observed around 2 meV.



Figure 2: Energy scan of the spin-liquid scattering at low (blue) and high (red) temperature showing magnetic scattering extending out to well above 4 meV at low T.

References

- 1. Anderson, P.W. et al. Phys. Rev. Lett. 1987, 58, 2790.
- 2. Fåk, B. et al. Phys. Rev. Lett. 2012, 109, 37208.
- 3. Han, T-H. et al. Nature 2012, 492, 406.
- 4. de Vries, M.A. et al. Phys. Rev. Lett. 2009, 103, 237201.
- 5. Helton, J.S. et al. Phys. Rev. Lett. 2007, 98, 107204.
- 6. Colman, R.H. et al. Chem. Mater. 2010, 22, 5774.
- 7. Colman, R.H. et al. Chem. Mater. 2011, 23, 1811–1817.
- 8. Boldrin, D., Fåk, B. et al., Phys. Rev. B 2015, 91, 220408(R).
- 9. Messio, L. et al. Phys. Rev. B 2011, 83, 184401.
- 10. Kermarrec, E. et al. Phys. Rev. B 2009, 84, 100401.